



9411 Corsair Road Frankfort, IL 60423 1-800-552-0299 Phone 1-815-464-5650 Fax

EMERGENCY PHONE 1-800-255-3924 TECHNICAL DATA SHEETS MP 54750

Description:

MP 54750 is a two part unfilled epoxy structural adhesive designed for bonding application requiring conformance to the Code of Federal Regulations Title 21 175.105 (Adhesives) and 175.300 (Resinous and polymeric coatings)¹. It cures completely at room temperature to a tough, semi-rigid polymer. It has good wetting and adhesion to most surfaces and has a free flowing viscosity. It has very good resistance to water, acids and bases and most organic solvents.

It was especially formulated to a 1A:1B volume mix ratio for use in side-by-side dispensing cartridges and meter/mix and dispense equipment. **MP 54750** will reach full cure at room temperature within 24 –48 hours. Cure time can be accelerated by the application of heat. Times and temperatures from 2 hours at 150F to 10 minutes at 225F are typical for most applications. Time to heat substrate must be taken into account. Cooler temperatures will also extend work time and increase cure times.

INSTRUCTIONS:

- 1) Bring to room temperature before use.
- 2) Weight and mix parts A and B accurately and thoroughly, scraping sides of container often.
- 3) Allow to cure undisturbed.

TYPICAL PROPERTIES:

All properties given are at 25C unless otherwise noted.

Color Viscosity Specific Gravity	Part A Part B Mixed Part A Part B Mixed	Clear 12,000 cps 18,000 cps 15,000 cps 1.16 0.98 1.10
Pot Life Mass	60 - 90 minutes 50 grams	
Hardness Shore - D Tensile Elongation Tensile Strength Tensile Strength Lap Shear (Al to Al) Dielectric Constant 25C, 100Hz) Dielectric Strength Volume Resistivity		80 8 - 10% * 7000 psi 2500 psi 3.5 * 410 v/mil 8.3 x 10 ¹⁴ ohm-cm
<u>MIX RATIO:</u> Mix Ratio (Part A to B): by weight by volume		100 to 85 1 to 1
CURE SCHEDULE:		24 – 72 hours at 77°F or 2 hours @ 150°F
SHELF LIFE:		

12 Months

Engineering Excellence

For technical information and support call 1-800-552-0299 or visit our website at

