

Revised  
January 2003



9411 Corsair Road  
Frankfort, IL 60423  
1-800-552-0299 Phone  
1-815-464-5650 Fax

**EMERGENCY PHONE 1-800-255-3924**

## TECHNICAL DATA SHEETS

### NI 100

#### Description:

**NI 100** is a Low odor/Low bloom instant adhesive. **NI 100** greatly reduces frosting on parts and the need for sophisticated ventilation.

#### Physical Properties:

COLOR: Clear  
VISCOSITY: 100cps  
BASE: Butyl  
STRENGTH: 1900 / 3000  
TEMPERATURE RANGE: - 65 - 180°F  
CURE SPEED: 8 seconds  
(FIXTURE)  
  
SPECIFIC GRAVITY 1.05  
SOLUBLE IN: Remove Debonder

#### Storage

The NI series is ideally stored in a cold, dry location in unopened containers. Optimal storage temperature is under 50°F. To prevent contamination of unused product, do not return any material to its original container. For specific shelf life contact Adhesive Systems Inc.

#### Handling Characteristics:

Shear Strength, ASTM D1002, DIN 53283	Value	Range
Girt Blasted Steel, N/mm <sup>2</sup> (psi)	20 (2900)	14 to 22 (2030 to 3190)
Etched Aluminum, N/mm <sup>2</sup> (psi)	14 (1920)	9 to 15 (1305 to 2175)
ABS, N/mm <sup>2</sup> *	>7 (>885)	
PVC, N/mm <sup>2</sup> *	>5 (>640)	
Polycarbonate, N/mm <sup>2</sup> *	>5 (>790)	
Phenolic, N/mm <sup>2</sup> *	11 (155)	5 to 15 (700 to 2200)
Neoprene rubber, N/mm <sup>2</sup> *	>11 (>1510)	
Nitrile rubber, N/mm <sup>2</sup> *	>11 (>1510)	
Tensile Strength, ASTM D2095, DIN 53283		
Grit Blasted Steel, N/mm <sup>2</sup> (psi)	18.5 (2735)	14 to 25 (1400 to 3600)

\* Substrate Failure

### Engineering Excellence

For technical information  
and support call **1-800-552-0299** or visit our website at

**[www.instantca.com](http://www.instantca.com)**