

Revised  
January 2003



9411 Corsair Road  
Frankfort, IL 60423  
1-800-552-0299 Phone  
1-815-464-5650 Fax

**EMERGENCY PHONE 1-800-255-3924**

## TECHNICAL DATA SHEETS

### NI 5

#### Description:

**NI 5** is a Low odor/Low bloom instant adhesive.

**NI 5** greatly reduces frosting on parts and the need for sophisticated ventilation.

#### Physical Properties:

COLOR:	Clear
VISCOSITY:	5cps
BASE:	Butyl
STRENGTH:	1900 / 3000
TEMPERATURE RANGE:	- 65 - 180°F
CURE SPEED: (FIXTURE)	7 seconds
SPECIFIC GRAVITY	1.05
SOLUBLE IN:	Remove Debonder

#### Handling Characteristics:

Shear Strength, ASTM D1002, DIN 53283	Value	Range
Grit Blasted Steel, N/mm <sup>2</sup> (psi)	20 (2900)	14 to 22 (2030 to 3190)
Etched Aluminum, N/mm <sup>2</sup> (psi)	14 (1920)	9 to 15 (1305 to 2175)
ABS, N/mm <sup>2</sup> * (psi)	>7 (>885)	
PVC, N/mm <sup>2</sup> * (psi)	>5 (>640)	
Polycarbonate, N/mm <sup>2</sup> * (psi)	>5 (>790)	
Phenolic, N/mm <sup>2</sup> * (psi)	11 (155)	5 to 15 (700 to 2200)
Neoprene rubber, N/mm <sup>2</sup> * (psi)	>11 (>1510)	
Nitrile rubber, N/mm <sup>2</sup> * (psi)	>11 (>1510)	
Tensile Strength, ASTM D2095, DIN 53283		
Grit Blasted Steel, N/mm <sup>2</sup> (psi)	18.5 (2735)	14 to 25 (1400 to 3600)

\* Substrate Failure

#### Storage

The NI series is ideally stored in a cold, dry location in unopened containers. Optimal storage temperature is under 50°F. To prevent contamination of unused product, do not return any material to its original container. For specific shelf life contact Adhesive Systems Inc.

### Engineering Excellence

For technical information  
and support call **1-800-552-0299** or visit our website at

**[www.instantca.com](http://www.instantca.com)**