



Premium SP-9020

SP-9020 rigid ABS thermoplastic sheet offers customized gloss with no sacrifice in performance. Exact resin blends are precisely controlled to achieve gloss, impact and total conformance to customer specifications.

Premium SP-9020 Data

Test	Condition	Units	Value
Specific Gravity	ASTM D792	g/cm ³	1.03
Tensile Modulus	ASTM D638	psi	310,000
Tensile Strength	ASTM D638	psi	5,400
Flexural Modulus	ASTM D790	psi	300,000
Flexural Strength	ASTM D790	psi	9,600
Izod Impact	ASTM D256	Ft-lbs/in.	8.0
	(73°F, -40°C)		4.0
Falling Dart Impact	ASTM D3029	Ft-lbs	35
	(73°F, -40°C)		23
Heat Deflection Temperature	ASTM D648	°F	195
Hardness	ASTM D785	Rockwell R	105
Gardner Gloss	ASTM D523	%	90
Flammability Rating	MVSS 302		Passes
	UL94 HB		Passes

Spartech warrants that its products conform to its published specifications in effect at the time of sale, but Spartech expressly disclaims any warranties of the merchantability and of fitness for a particular purpose with respect to its products. The values shown above are representative of values that have been obtained in the testing of samples produced in various colors. Each user of the material should conduct his own testing and evaluation to determine the effectiveness, safety, and suitability of the material for its particular use.

